



LINDQUIST STEELS, INC.

TOOL STEEL SPECIALISTS

Connecticut

1•800•243•9637
Fax: 203•386•0132
sales@lindquiststeels.com

South Carolina

1•800•845•7052
Fax: 803•794•6658
sales-sc@lindquiststeels.com

Tennessee

1•866•489•6417
Fax: 865•938•0342
sales-tn@lindquiststeels.com

TECHNICAL BULLETIN

10 PM/A11 TOOL STEEL

Typical Analysis:	Carbon 2.40/2.50	Mang. 0.35/0.60	Silicon 0.75/1.10	Chromium 4.75/5.75	Moly. 1.10/1.50	Vanadium 9.25/10.25	Sulphur 0.05/0.09
-------------------	---------------------	--------------------	----------------------	-----------------------	--------------------	------------------------	----------------------

Color Code: Black/White Stripe



DESCRIPTION

10 PM/A11 tool steel is a high vanadium tool steel produced using the powder metal process. This grade possesses wear resistance superior to most other tool steels, including the high speed steels, along with good strength and toughness characteristics.

Many of the benefits realized in the use of powdered metals are a direct result of the refined microstructure (smaller, more uniformly distributed carbide particles and a finer grain size) and the lack of segregation in the powder metallurgy product. These advantages include ease of grinding, improved response to heat treatment, greater wear resistance, and increased toughness of the finished tool.

SIZE CHANGE IN HARDENING — 10 PM/A11 tool steel changes size only slightly after hardening. An expansion of about .0004 inches/inch is typical. Tools will open up slightly in the ID and expand on OD.

CHARACTERISTICS

MACHINABILITY — The machinability of 10 PM/A11 tool steel in the annealed condition may be rated between 35 to 40% of 1% carbon tool steel. Tooling provider's recommendations for cutting fluids should be followed.

Due to the presence of the fine, uniformly distributed carbides, the grindability of 10 PM/A11 tool steel is relatively good. Grinding wheel supplier's recommendations should be followed. Grinding wheels containing ceramic particles may provide improved performance.

One can easily EDM 10 PM/A11 tool steel using proper precautions to prevent and/or remove the "white layer".

THERMAL PROCESSING

DECARBURIZATION — Like all high carbon steels, 10 PM/A11 tool steel is somewhat susceptible to decarburization in hardening. Means of preventing decarburization are well known. Modern furnaces which employ protective environments, such as protective atmosphere furnaces, salt pots, fluidized bed furnaces and vacuum furnaces, should present no difficulty with decarburization of this alloy.

FORGING — Heat slowly to 2000/2100°F (1093/1149°C). Do not work below 1700°F (927°C). Reheat as necessary. Cool forgings slowly and anneal immediately upon cooling.

NORMALIZING — Normalizing is not recommended.

ANNEALING — Heat slowly to 1600/1650°F (871/889°C), hold for 2 hours, cool slowly at a rate of 20/40°F (11/22°C) per hour to 1000°F (538°C), then air cool. Typical annealed hardness will be 255 to 277 Brinell.

STRESS RELIEVING — To relieve machining stresses for greater accuracy in hardening, first, rough machine, then heat to a temperature of 1150/1250°F (621/677°C), equalize, and cool slowly in still air.

HARDENING — 10 PM/A11 tool steel should be heat treated using proper precautions to prevent decarburization. First, preheat to 1500/1550°F (816/843°C), equalize and transfer to a furnace maintained at the desired hardening temperature.

TOUGH TREATMENT — Austenitize at 1950°F (1066°C) for 30 to 60 minutes then air cool. Temper immediately to Rockwell HRC 58/61.

INTERMEDIATE TREATMENT — Austenitize at 2050°F (1121°C) for 15 to 30 minutes, fan air cool, quench in oil or step quench in salt. Temper immediately to Rockwell HRC 60/62.

WEAR TREATMENT — Austenitize at 2150°F (1177°C) for 5 to 10 minutes, oil quench. If vacuum quench is desired, furnaces should have 4 bar minimum capability. Temper immediately to Rockwell HRC 63/65.

TEMPERING — Tools should be tempered immediately after completion of the hardening treatment. The tempering temperature may be adjusted according to the hardness desired. Tempering usually performed in the temperature range of 1000/1100°F (538/593°C).

Triple tempering and/or refrigeration at -100°F (-73°C) is suggested when hardening is performed above 2100°F (1149°C). If refrigeration is used, tools should be refrigerated immediately after the first temper.

The effects of various hardening and tempering temperatures are shown in the following chart.

Tempering Temp °F/°C	Average Rockwell C Hardness		
	Austenitized 1950°F (1066°C)	Austenitized 2050°F (1121°C)	Austenitized 2150°F (1177°C)
As Quenched	64.5	64.0	62.5
1000/538	60.0	61.0	64.0
1025/551	59.0	60.0	62.0
1050/566	55.0	58.0	60.0
1100/593	50.0	52.0	54.0
1150/621	44.0	45.0	46.0

www.lindquiststeels.com

